

ALGUNAS COMPOSICIONES DE ALEACIONES - SOME ALLOYS COMPOSITIONS

Algunas composiciones de aleaciones Some alloys compositions		
Latón	Brass	Cobre (Copper) 86%, Zinc 12%, Estaño (Tin) 2%
Bonce	Bronze	Cobre (Copper) 88%, Estaño (Tin) 10% Plata (Silver) 13%
Oro 10 KY	Gold 10 KY	Oro (Gold) 41.7%, Cobre (Copper) 40.89% Plata (Silver) 11.7%, Zinc 5.8%
Oro 10 Kw.	Gold 10 Kw.	Oro (Gold) 41.7%, Cobre (Copper) 32.82% Zinc 8.4%, Nickel 17.08%
Oro 14 Ky.	Gold 14 Ky.	Oro (Gold) 58.3%, Cobre (Copper) 30% Plata (Silver) 5%, Zinc 6.67%
Oro 14 Kw.	Gold 14 Kw.	Oro (Gold) 58.3%, Cobre (Copper) 22.1% Zinc 8.77%, Nickel 10.80%
Oro 18 Kw.	Gold 18 Kw.	Oro (Gold) 75%, Cobre (Copper) 10% Plata (Silver) 15%
Oro 18 KY.	Gold 18 KY.	Oro (Gold) 75%, Cobre (Copper) 7% Zinc 4%, Nickel 14%
Oro 14K verde	Gold 14K green	Oro (Gold) 58.3%, Cobre (Copper) 8.97% Plata (Silver) 32.5%, Zinc 2%
Oro 18K rojo	Gold 18K red	Oro (Gold) 75%, Cobre (Copper) 25%



HISPANA

de Maquinaria, S.A.

Tel. +34 93 3091707 Fax. + 34 93 3090702

e-mail: hispana@hispanaspain.com

internet: <http://www.hispanaspain.com>

Calle Pallars, 85 - 91 - Barcelona 08018 - España (Spain)